

Samarium Cobalt - Sintered

Material	Grade	Remanence Br (mT)		Normal coercivity H _{cb} (kA/m)		Intrinsic coercivity H _{cJ} (kA/m)	Energy density (BH) _{max} KJ/m ³		Max. operating temp.	Temp Coeff. Br	Temp Coeff. H _{cJ}
		min	max	min	max	min - max	min	max	°C	%/°C	%/°C
SmCo5	YX-16	810	850	620	660	1.194 - 1.830	110	127	250	-0.50	-0.30
	YX-18	850	900	660	700	1.194 - 1.830	127	143	250	-0.50	-0.30
	YX-20	900	940	676	725	1.194 - 1.830	150	167	250	-0.50	-0.30
	YX-22	920	960	710	748	1.194 - 1.830	160	175	250	-0.50	-0.30
	YX-24	960	1.000	730	770	1.194 - 1.830	175	190	250	-0.50	-0.30
	YX-16s	790	840	620	660	≥1.830	118	135	250	-0.035	-0.28
	YX-18s	840	890	660	700	≥1.830	135	151	250	-0.040	-0.28
	YX-20s	890	930	684	732	≥1.830	150	167	250	-0.045	-0.28
	YX-22s	920	960	710	756	≥1.830	167	183	250	-0.045	-0.28
	YX-24s	960	1.000	740	788	≥1.830	183	199	250	-0.045	-0.28
SmCo5 of low Temp. Coeff. (SmGd)Co5	LTC(YX-10)	620	660	485	517	≥1.830	75	88	20-100 100-200 200-300	+0,0156 +0,0087 +0,0007	
Sm2Co17	YXG-24H	950	1.020	692	764	≥1.990	175	191	350	-0.025	-0.20
	YXG-26H	1.020	1.050	748	796	≥1.990	191	207	350	-0.030	-0.20
	YXG-28H	1.030	1.080	756	812	≥1.990	207	223	350	-0.035	-0.20
	YXG-30H	1.080	1.100	788	835	≥1.990	223	239	350	-0.035	-0.20
	YXG-32H	1.100	1.130	812	860	≥1.990	231	255	350	-0.035	-0.20
	YXG-33H	1.120	1.160	845	890	≥1.990	239	263	350	-0.035	-0.20
	YXG-22	930	970	676	740	≥1.433	160	183	300	-0.020	-0.20
	YXG-24	950	1.020	692	764	≥1.433	175	191	300	-0.025	-0.20
	YXG-26	1.020	1.050	748	796	≥1.433	191	207	300	-0.030	-0.20
	YXG-28	1.030	1.080	756	812	≥1.433	207	223	300	-0.035	-0.20
	YXG-30	1.080	1.100	788	835	≥1.433	223	239	300	-0.035	-0.20
	YXG-32	1.100	1.130	812	860	≥1.433	231	255	300	-0.035	-0.20
	YXG-33	1.120	1.160	845	890	≥1.433	239	263	300	-0.035	-0.20
	YXG-35	1.160	1.200	868	908	≥1.433	255	278	300	-0.035	-0.20
	YXG-26M	1.020	1.050	676	780	955-1.433	191	207	300	-0.035	-0.20
	YXG-28M	1.030	1.080	676	796	955-1.433	207	220	300	-0.035	-0.20
	YXG-30M	1.080	1.100	676	835	955-1.433	220	240	300	-0.035	-0.20
	YXG-32M	1.100	1.130	676	852	955-1.433	230	255	300	-0.035	-0.20
	YXG-24L	950	1.020	541	716	636-955	175	191	250	-0.025	-0.20
	YXG-26L	1.020	1.050	541	748	636-955	191	207	250	-0.035	-0.20
	YXG-28L	1.030	1.080	541	764	636-955	207	220	250	-0.035	-0.20
	YXG-30L	1.080	1.150	541	796	636-955	220	240	250	-0.035	-0.20
	YXG-32L	1.100	1.150	541	812	636-955	230	255	250	-0.035	-0.20
Sm2Co17 of low Temp. Coeff. (SmEr)2 (CoTm)17	LTC(YXG-18)	840	890	629	668	≥1.433	135	151	300	-0,001	-0,25
	LTC(YXG-20)	890	940	660	708	≥1.433	151	167	300	-0,007	-0,25
	LTC(YXG-22)	940	980	692	740	≥1.433	167	183	300	-0,01	-0,25
	HT400(YXG-24)	990	1.040	740	788	≥1.830	183	199	400	-0,035	-0,1
	HT450(YXG-22)	940	990	700	748	≥1.830	167	183	450	-0,035	-0,1
	HT500(YXG-20)	890	940	660	708	≥1.830	151	167	500	-0,035	-0,1

Physical properties at room temperature (20°C)

Density:	8,3-8,4g/cm ³
Vickers Hardness:	450-600Hv
Tensile strength:	35-40 Mpa
Curie Temperature:	700-800°C
Temp.Coeff. of Br:	See individual material data
Electrical resistivity:	5-9 x 10 ⁻⁵ Ω cm
Coeff. Of Thermal Exp	4 x 10 ⁻⁶ /°C
Compressibility:	800-1000 Mpa
Max. operating temp.	20 - 500 °C
Flexure Strength:	150-180 Mpa

Disclaimer: Magnetic and mechanical performance may vary depending on the magnet's geometry and the production methods used. The figures provided here serve as general reference values and do not constitute guaranteed specifications. Performance in practical applications can differ. MagnetIQTechnologies reserve the right to modify material properties and performance criteria without prior notice.